

OK Autrod 5356

OK Autrod 5356 is the most widely used welding alloy and can be classified as a general purpose type filler alloy. OK Autrod 5356 is typically chosen because of its relatively high shear strength. The 5XXX alloy base material, welded with OK Autrod 5356, with a weld pool chemistry greater than 3 % Mg and service temperatures in excess of 65°C are susceptible to stress corrosion cracking. The alloy is non-heat treatable.

Classifications Wire Electrode	SFA/AWS A5.10: ER5356 EN ISO 18273: S Al 5356 (AlMg5Cr(A))
Beteckning	JIS Z 3232: A53556 SFA/AWS A5.10: ER5356 EN ISO 18273: S Al 5356 (AlMg5Cr(A))
Godkännanden	ABS ER 5356 BV WB CE EN 13479 CWB ER5356 DB 61.039.01 DNV-GL 5356 JIS JIS Z 3232 LR WB/11 RINA WC (*) VdTUV 04664

Godkännanden baseras på fabriken lokaliserings. Vänligen kontakta ESAB för mer information.

Alloy Type	AlMg 5
-------------------	--------

Typical Wire Composition

Mn	Si	Cr	Al	Cu	Fe	Mg	Zn
0.13	0.05	0.12	94.560	0.01	0.13	4.9	0.01

Insmåtningsdata

Diameter	Ampere	Volt
0.8 mm	60-170 A	13-24 V
0.9 mm	60-170 A	13-24 V
1.0 mm	90-210 A	15-26 V
1.2 mm	140-260 A	20-29 V
1.6 mm	190-350 A	25-30 V
2.0 mm	-	-
2.4 mm	280-400 A	26-31 V